

**ТЕХНИЧЕСКИЕ УСЛОВИЯ
ОКСИДЫ АЛЮМИНИЯ
РЕАКТИВНЫЕ**

МАРКА		SALOX S1R	SALOX S50SG	SALOX S155GS1	SALOX S1FGS1	SALOX S1FG	SALOX S1SG
Al ₂ O ₃ *	%	min. 91	min. 99.4	min. 99.4	min. 99.5	min. 99.5	min. 99.5
SiO ₂	%	max. 0.04	max. 0.02	max. 0.02	max. 0.04	max. 0.04	max. 0.04
Fe ₂ O ₃	%	max. 0.04	max. 0.03	max. 0.03	max. 0.04	max. 0.04	max. 0.04
Na ₂ O total	%	max. 0.4	max. 0.3	max. 0.3	max. 0.3	max. 0.3	max. 0.3
CaO	%		max. 0.04	max. 0.04	max. 0.04	max. 0.04	max. 0.04
ППП	%	max. 8	max. 0.5	max. 0.5	max. 0.2	max. 0.02	max. 0.02
> 45 μm (мокрый ситовый ан-з)	%	max. 1	max. 1	max. 1	max. 1	max. 3	max. 0.1
Средняя величина частиц d ₅₀	μm	7 – 13	2 – 5	2 – 5	2 – 5	3 – 6	3 – 6
Средняя величина частиц d ₉₀	μm	max. 1	max. 1	max. 1	max. 1		
Удельная поверхность (BET)	m ² /g	140 – 190	12 – 30	6 – 12	max. 2	max. 1.5	max. 1.5